

Date Rcvd	Request By	Tested by	Brand ID	Moisture (%)	Ash (%)	HHV _{as rec} (BTU/lb)	HHV _{BD} (BTU/lb)	Chlorine (ppm)	Bulk Density (lb/ft ³)	Fines (%)	Durability (%)	% by Weight < 1.5" in	Max Length (inches)	Diam Avg (inches)
04/06/2011	Marwood	CBEC	Comfy Cozy	3.67	0.31	8537	8862	34	45.6	0.21	97.8	0.00	1.28	0.255
04/27/2011	Marwood	CBEC	Comfy Cozy	4.16	0.39	8238	8596	11	46.7	0.19	98.2	0.00	1.35	0.256
06/02/2011	Marwood	CBEC	Comfy Cozy	4.13	0.46	8315	8673	32	46.5	0.37	97.8	0.15	1.74	0.253
07/04/2011	Marwood	CBEC	Comfy Cozy	5.53	0.45	8133	8609	6.5	46.2	0.19	98.4	0.00	1.13	0.254
07/15/2011	Marwood	CBEC	Comfy Cozy	6.35	0.26	8121	8672	8.1	46.3	0.28	98.3	0.00	1.26	0.253
09/08/2011	Marwood	CBEC	Comfy Cozy	5.72	0.61	8007	8493	10.5	44	0.21	98.2	0.27	1.65	0.253
09/28/2011	Marwood	CBEC	Comfy Cozy	2.53	0.68	7957	8164	8.4	47.4	0.39	97	0.13	1.51	0.253
11/09/2011	Marwood	CBEC	Comfy Cozy	4.17	0.43	8246	8605	11.9	46.7	0.22	98.1	0.00	1.32	0.252
12/02/2011	Marwood	CBEC	Comfy Cozy	4.75	0.66	8089	8493	11.5	46.2	0.18	98.3	0.13	1.59	0.254
02/08/2012	Marwood	CBEC	Comfy Cozy	4.42	0.53	8270	8652	15.2	47.9	0.15	98.8	0.32	1.91	0.251
03/16/2012	Marwood	CBEC	Comfy Cozy	4.96	0.25	8330	8765	46.4	46.4	0.22	98.3	0	1.40	0.253
09/18/2012	Marwood	CBEC	Comfy Cozy	6.67	0.20	8095	8657	17.1	44.7	0.11	98.6	0.20	1.61	0.253
12/03/2012	Marwood	CBEC	Comfy Cozy	4.42	1.0	8279	8651	32.1	44.7	0.10	98.4	0.07	1.45	0.253
01/02/2013	Marwood	CBEC	Comfy Cozy	3.76	1.2	8342	8672	25.5	44.2	0.17	98.4	0.15	1.69	0.250
04/08/2013	Marwood	CBEC	Comfy Cozy	4.3	0.53	8133	8498	35.7	44.2	0.2	97.7	0	1.11	0.255
08/28/2013	Marwood	CBEC	Comfy Cozy	6.8	1.1	8140	8734	38.5	42.8	0.23	97.4	0	1.25	0.257
			Average	4.77	0.57	8202	8612	22	45.7	0.21	98.1	0.09	1.45	0.253